



JLW-308

Bi-Directional Filament Tape

| Physical Properties | Standard | Metric | Test Method | |
|---------------------|------------------|------------|-------------|-------------|
| Reinforcement | Fiberglass | | | |
| Adhesive | Synthetic Rubber | | | |
| Backing | PET | | | |
| Color | Clear | | | |
| Total Thickness | 6.7 mils | 0.17 mm | ASTM D-3652 | GB/T7125 |
| Peel Adhesion 90° | 0 | 0 | ASTM D-3330 | GB/T2792 |
| Holding Power | 0 | 0 | ASTM D-3654 | GB/T4851 |
| Tensile strength | 45 lbs/in | 200 N/25mm | ASTM D-3759 | GB/T7753 |
| Elongation at Break | 3-5% | 3-5% | ASTM D-3759 | GB/T7753 |
| Service Tem.--Mini | 32°F | 0°C | BC/BD-220SE | BC/BD-220SE |
| Service Tem.--Max | 122°F | 50°C | DHG-9055A | DHG-9055A |

DESCRIPTION

JLW-308 Backed with PET film and reinforced with glass fiber. It's reinforced bi-directional filament tape; abrasion-resistance and moisture resistance. No adhesive; suitable for internal bundling and fixing.

PERFORMANCE FEATURES

JLW-308 is a transparent reinforced bi-directional filament tape. Glass fiber contributes higher tensile strength.No adhesive; generating bi-directionally strengthened effect; high resistance to abrasion; impact resistance.

STORAGE CONDITION

It's recommended to store in clean and dry place. Damaged packaging shall be prevented. Not stored with volatile solvent. The temperature of storage shall be 4°C to 26°C and the humidity shall be between 40% and 50%. Rotate inventory recommended.

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of JIALONG product. JIALONG does not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. JIALONG strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. JIALONG assumes no responsibility for any damage or injury sustained as a result of the use of its products.

FUJIAN JIALONG ADHESIVE TAPE CO., LTD.

No.11 Xiazhai Road, Jiulong Industry Park, Hua An, Zhangzhou, Fujian 363000 China.
Tel:+86-592-207-5506

info@jl3tape.com <http://www.jl3tape.com>

