



JLT-6614-2

Mono-Directional Clean Removal Filament Tape

| Physical Properties | Standard | Metric | Test Method | |
|---------------------|------------------|-------------|-------------|-------------|
| Reinforcement | Chemical Fiber | | | |
| Adhesive | Synthetic Rubber | | | |
| Backing | PET | | | |
| Color | Clear | | | |
| Total Thickness | 9.1 mils | 0.23 mm | ASTM D-3652 | GB/T7125 |
| Peel Adhesion 90° | 65 oz/in | 18 N/25 mm | ASTM D-3330 | GB/T2792 |
| Holding Power | 48±5 h | 48±5 h | ASTM D-3654 | GB/T4851 |
| Tensile strength | 191 lbs/in | 850 N/25 mm | ASTM D-3759 | GB/T7753 |
| Elongation at Break | 30±3% | 30±3% | ASTM D-3759 | GB/T7753 |
| Service Tem.--Mini | 14°F | -10°C | BC/BD-220SE | BC/BD-220SE |
| Service Tem.--Max | 176°F | 80°C | DHG-9055A | DHG-9055A |

Description

JLT-6614-2 is a high-strength unidirectional fiber tape based on PET film and chemical fibers. It features high adhesion and long-lasting holding power, making it suitable for heavy-duty bundling, pipe wrapping, pallet securing, and reinforcing transport cartons and other packaging applications.

Performance Features

JLT-6614-2 is a transparent, high-strength fiber tape. The embedded chemical fibers provide significantly improved tensile strength compared to conventional tapes. It uses a modified synthetic rubber adhesive, ensuring more effective bundling of components and parts during manufacturing and transportation. The tape offers excellent wear resistance, impact resistance, and high holding power.

Shelf Life

Up to one years from the date of shipment with proper storage.

Storage Condition

It is recommended to store the product in a clean, dry environment to prevent packaging damage. Avoid placing it near volatile solvents. The optimal storage temperature is between 39-79°F (4-26°C), with a relative humidity of 40%-50%. Rotate inventory regularly to maintain product quality.

The test results provided above represent average values obtained under laboratory conditions and are intended for general reference only. JL3 does not guarantee the accuracy, completeness, or performance consistency of these results. These values do not constitute a warranty, either express or implied, including but not limited to warranties of performance, safety, or fitness for a particular purpose—whether the product is used alone or in combination with other materials. JL3 strongly recommends that users conduct independent testing to determine the product's suitability for their specific application prior to use. JL3 assumes no liability for any damage, loss, or injury arising from the use of this product. All sales are subject to JL3's standard terms and conditions. Product specifications and information are subject to change without prior notice.

Fujian Jialong Adhesive Tape Co.,Ltd.

No. 11 Xiazhai Road, Jiulong Industrial Park, Hua An Economic Development Zone, Hua An, Zhangzhou, Fujian 363000 China.
 Tel: +86 596-728-0001
 info@jl3tape.com
 http://www.jl3tape.com

